

### Morphology of sodium bromate (NaBrO3) under the influence of purified sodium dithionate (Na2S2O6)

M. Schindler, Clément Brandel, G. Coquerel

#### ▶ To cite this version:

M. Schindler, Clément Brandel, G. Coquerel. Morphology of sodium bromate (NaBrO3) under the influence of purified sodium dithionate (Na2S2O6). 43èmes JEEP, Mar 2017, Barcelone, Spain. hal-01938524

#### HAL Id: hal-01938524 https://normandie-univ.hal.science/hal-01938524

Submitted on 12 Dec 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



# Morphology of sodium bromate (NaBrO<sub>3</sub>) under the influence of purified sodium dithionate (Na<sub>2</sub>S<sub>2</sub>O<sub>6</sub>)







Manon SCHINDLER\*, Clément BRANDEL, Gérard COQUEREL

Normandie Univ, Laboratoire SMS-EA3233, Univ Rouen, F76821, Mont-Saint-Aignan, France.

\*manon.schindler@etu.univ-rouen.fr




## INTRODUCTION


 $NaClO_3$  and  $NaBrO_3$  present **isomorphous structures** (same space group  $P2_13$  and same atomic positions in the unit cell). Although the two substances are achiral, crystals of NaClO<sub>3</sub> and NaBrO<sub>3</sub> both show supramolecular chirality. However, the crystal habits of NaClO<sub>3</sub> and NaBrO<sub>3</sub> differ: NaClO<sub>3</sub> crystals exhibit large cubic {100} faces while NaBrO<sub>3</sub> crystals exhibit tetrahedral {111} faces.<sup>2</sup>

#### SUPRAMOLECULAR CHIRALITY

The use of a pair of polarizer can easily evidence the occurrence of levo and dextro enantiomorphic crystals.


NaBrO<sub>3</sub>







Crystals of NaBrO<sub>3</sub> from aqueous solution observed under polarized light.

# NaClO<sub>3</sub>








Crystals of NaClO<sub>3</sub> from aqueous solution observed under polarized light.


# INFLUENCE OF Na<sub>2</sub>S<sub>2</sub>O<sub>6</sub> ON NaClO<sub>3</sub>

Crystallization of NaClO<sub>3</sub> from aqueous solution in presence of  $Na_2S_2O_6$  (molar ratio 1/1000)

\* Habit modification of NaClO<sub>3</sub> by addition of  $Na_2S_2O_6$ 

Enhancing the {111} tetrahedral faces and suppressing the {001}cubic ones <sup>3</sup>





Crystal of NaClO<sub>3</sub> showing the tetrahedral morphology. Obtained by evaporation of solvent at room temperature.in presence of  $Na_2S_2O_6$ .

**\*** Formation of NaClO<sub>3</sub> twin of opposite handedness<sup>3</sup>



Twinned crystal of NaClO<sub>3</sub> showing two opposite handedness obtained by evaporation of solvent at room temperature in presence of  $Na_2S_2O_6$ .



Effect of sodium dithionate on sodium bromate?

# SYNTHESIS & CHARACTERIZATION OF Na<sub>2</sub>S<sub>2</sub>O<sub>6</sub>

As the sodium dithionate is not easily available,  $Na_2S_2O_6$  was synthesized. The synthesized product has been compared with the commercial batch.

# Synthesis<sup>4</sup>

#### **Reaction involved:**

Step I:  $Na_2SO_3 + 2AgNO_3 \rightarrow Ag_2SO_3 + 2NaNO_3$ 

Step II (oxidation-reduction reaction)\*:  $Ag_2SO_3 + Na_2SO_3 \rightarrow Na_2S_2O_6 + 2Ag_2SO_3 + Na_2SO_3 \rightarrow Na_2S_2O_6 + 2Ag_2SO_8 + Na_2SO_8 + Na_2SO$ 


**Experiment:** Reagents mixture is kept 30 min under stirring and boiling. White precipitate of Ag<sub>2</sub>SO<sub>3</sub> disappears and Ag crystallizes. After filtration of silver, solution of dithionate is concentrated by evaporation of solvent. Crystallization of dihydrated dithionate is induced by addition of antisolvent (ethanol and acetone). Yield: 75%

\*Involved oxidation-reduction reaction: Strongest oxidizing agent  $(Ag^+)$ reacts with the weakest reducing agent ( $SO_3^{2-}$ ).


$$2Ag^{+} + 2e^{-} \rightarrow 2Ag$$
  $E^{\circ} = 0,800 \text{ V}$   
 $2SO_{3}^{(+IV)} \xrightarrow{(+V)} S_{2}O_{6}^{2-} + 2e^{-}$   $E^{\circ} = 0,514 \text{ V}$ 

 $2Ag^{+} + SO_{3}^{2-} + 2Na^{+} + SO_{3}^{2-} \rightarrow 2Na^{+} + S_{2}O_{6}^{2-} + 2Ag$ 

# Characterization of synthesized product



TG-DSC of the commercial batch (red) and the synthesized product (green).




Na<sub>2</sub>S<sub>2</sub>O<sub>6</sub>,2H<sub>2</sub>O recrystallized in water Na<sub>2</sub>S<sub>2</sub>O<sub>6</sub>,2H<sub>2</sub>O commercial batch

2θ (°) XRPD patterns of commercial batch (in black) and synthesized product (in red)

→ Commercial batch and synthesized product are sodium dithionate dihydrate.

→ Dehydration occurs at 90°C as described in literature.<sup>5</sup>



DSC analyses of different samples of  $Na_2S_2O_6$ . Comparison of different purification of synthesized product. (heating rate: 5K/min, closed crucibles)


 $\rightarrow$  Recrystallization in water is more efficient to purify Na<sub>2</sub>S<sub>2</sub>O<sub>6</sub>; the drawback is the low yield (47%).

#### THE MORPHOLOGIES OF SODIUM BROMATE<sup>3</sup>



→ No significant effect of sodium dithionate on the typical trigonal form of sodium bromate

Crystal of NaBrO<sub>3</sub> obtained from aqueous solution in presence of  $Na_2S_2O_6$  (molar ratio 1/1000) by evaporation of solvent, at room temperature



Supersaturation In(C/Ce)

→ At high temperature and high supersaturation, NaBrO<sub>3</sub> crystals can present a cubic habit. <sup>6</sup>

 $\rightarrow$  Effect of Na<sub>2</sub>S<sub>2</sub>O<sub>6</sub> on cubic morphology of NaBrO<sub>3</sub>?


Morphodrome of  $NaBrO_3$  as a function of the crystallization temperature and supersaturation<sup>6</sup>

In sealed vial, required amount of NaBrO<sub>3</sub> to achieve desired supersaturation is dissolved in water and then cooled to crystallization temperature. Without seeding, crystallization occurs in few hours.

supersaturation: 1.05



Crystals of pure  $NaBrO_3$ .



Crystals of NaBrO<sub>3</sub> in presence of  $Na_2S_2O_6$ (molar ratio 0,3%).

- → No expected cubic crystals at high temperature and high supersaturation. Crystallization is not well controlled.
- $\rightarrow$  Na<sub>2</sub>S<sub>2</sub>O<sub>6</sub> seems to lead to twinned crystals.
- → Effect on handedness ?

#### **PROSPECTS**

- **Synthesis and characterization of Na<sub>2</sub>S<sub>2</sub>O<sub>6</sub>**
- Improve yield of synthesis and recrystallization
  - **❖** NaBrO<sub>3</sub>/ Na<sub>2</sub>S<sub>2</sub>O<sub>6</sub> system
- Reconsider experimental conditions to well control of NaBrO<sub>3</sub> crystallization
- What will be the effect of Na<sub>2</sub>S<sub>2</sub>O<sub>6</sub> on expected cubic crystals of NaBrO<sub>3</sub>? Will effects be the same (twins by inversion) than on NaClO<sub>3</sub> cubic crystals?

## **AKNOWLEDGMENTS**

This work was funded by the Normandy region and European regional development fund (FEDER).

#### References:

- [1] Kipping, F. S., Pope, W. J., J. Chem. Soc. Trans., 73, 606–617 (1898).
- [2] Surender, V., Arundhathi, N., Rao, K. K., Bull. Mater. Sci., 29 (5), 427–432 (2006).
- [3] Lan, Z.-P., Lai, X., Roberts, K., Klapper, H., Cryst. Growth Des. 14 (11), 6084–6092 (2014). [4] Schlessinger, G.G., Inorganic laboratory preparations, Chemical Publishing Company, 58-59 (1962).
- [5] Larson, D. W.; VanCleave, A. B. Can. J. Chem. 1963, 41 (2), 219–223.
- [6] Holcomb, E. R.; Inoue, T.; Nishioka, K. J. Cryst. Growth 1996, 158 (3), 336–339.