



Performance of particleboards based on annual plant byproducts bound with bio-adhesives

A. Mahieu, A. Vivet, C. Poilane, N. Leblanc

► To cite this version:

A. Mahieu, A. Vivet, C. Poilane, N. Leblanc. Performance of particleboards based on annual plant byproducts bound with bio-adhesives. *International Journal of Adhesion and Adhesives*, 2021, 107, pp.102847. 10.1016/j.ijadhadh.2021.102847 . hal-03345998

HAL Id: hal-03345998

<https://normandie-univ.hal.science/hal-03345998>

Submitted on 22 Mar 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial 4.0 International License

PERFORMANCE OF PARTICLEBOARDS BASED ON ANNUAL PLANT BYPRODUCTS BOUND WITH BIO-ADHESIVES

A. Mahieu^{1,2*}, A. Vivet³, C. Poilane³, N. Leblanc¹

¹ UniLaSalle, Transformations & Agroresources research unit, VAM²IN (EA 7519), 3 rue du Tronquet, CS 40118, 76134 Mont-Saint-Aignan Cedex, France.

² UniLaSalle – Ecole des Métiers de l'Environnement, campus de Ker Lann, 35170 Bruz, France.

³ Normandie University, 14032 Caen, France ; UNICAEN, CIMAP, 14032 Caen, France ; ENSICAEN, 14050 Caen, France ; CEA, UMR6252, 14070 Caen, France ; and CNRS UMR6252, 14050 Caen, France

*Corresponding author; angelique.mahieu@unilasalle.fr

Abstract

Because the timber market is more and more competitive, the particleboard manufacturers are looking for new sources of plant raw material. In the same time, the use of healthier, safer and more environmentally friendly materials becomes a priority in the building sector. In this context, using bio-based adhesives to bond the particles instead of the synthetic ones is an interesting alternative. In the same time agricultural byproducts as annual plant stems can be a sustainable alternative raw material. These resources are abundant, renewable and safe raw material. Moreover, their porous structure gives them interesting properties for building materials such as lightness and thermal insulation capacity. Two agricultural byproducts abundant in France have been studied: flax shives and sunflower bark. Particleboards were made at laboratory scale by thermocompression of the plant raw particles to a target density of 500 kg.m⁻³. The plant particles were bond by different methods:

- * without addition of any adhesive. In that case water was sprayed on the plant particles before the forming process and was evaporated during the thermocompression. It leads to extraction of soluble and lignocellulosic compounds from the agroresources that can act as adhesives.
- * with addition of a biobased adhesive based on casein, the protein from bovine milk, or based on a commercial caseinate, added at different ratios to the plant particles.

The effect of the type of agroresources, the particle size, the formulation of the biosourced adhesive, and its application are evaluated testing the physico-chemical properties of the particleboards: mechanical properties (bending test and internal bond), thermal properties, and behavior towards water and fire. Using a biobased adhesive improves the mechanical properties of the particleboards significantly compared to the version without added adhesive. Panels made with flax shives generally showed better

properties than with sunflower bark, so flax shives seem more suitable for particleboard manufacturing. But after optimization of the formulation and the process, both raw materials could be used with casein-based adhesive yielding efficient and fully biobased particleboards for applications such as furniture or door panels.

Keywords:

Totally biobased particleboards, agricultural byproducts, biobased adhesive, internal bond, plant particle adhesion.

1 INTRODUCTION

The exponentially growing consumption of raw materials in the building sector has a strong impact on the objectives of sustainable development, both environmental and socio-economic. More than in any other industry, the use of biomass feedstocks can provide a set of relevant responses to these needs. Renewable by nature, available in large quantities, sustainably stocking carbon, and generally requiring little production energy and local development vectors, agricultural raw materials are adapted to the manufacture of biosourced materials for the building sector as demonstrated by Vo et al. [1]. In addition, the problem of end-of-life management of building materials containing synthetic adhesives as binders due to the resistance of thermosetting resins to environmental degradation make the development of biobased materials coming from renewable resources a priority area of research as Laycock et al. [2] explain about the biodegradable polymers.

Agricultural productions generate many co-products that are potential sources of renewable raw materials to produce environmentally friendly materials. Optimal use of resources tends towards the valorization of the whole plant: seeds for food; long fibers for the textile industry or technical composite materials; straw, bark, pith, oilcake and other co-products as new sources of supply for the manufacture of materials that do not compete with food production. Numerous biobased compounds or coproducts can also be used as biosourced and biodegradable adhesives such as various polysaccharides, proteins, tannin, or plant resins.

In this context the development of particleboards based on agricultural by-products, such as annual plant stems, is an attractive alternative to wood. Many studies use agricultural residues as raw material for particleboards such as straw of various botanical origins. For example Klimek et al. [3] used miscanthus stalks, Zhang et al. [4] rice straw and coir fibers, Nguyen et al. [5] bamboo fibers, Mati-Baouche et al. [6] sunflower stalks, El Hajj et al. [7] and Privas et al. [8] flax shives, Viel et al. [9] hemp shives and corn cob, and Fiorelli et al. [10] green coconut and sugarcane bagasse fibers to produce particleboards. All these attempts are justified in their choice of agroresources by their renewability and availability in the location where the studies took place. These studies

vary in terms of the adhesive used and parameters of the thermocompression process. All conclude to the possibility of using agricultural residues in particleboards, but improvements are still necessary, especially concerning resistance to water and the elasticity modulus of these boards.

To use materials based on agricultural byproduct in a virtuous cycle, these materials must be compostable to be put back on the ground after utilization, and safe for human health. Classical synthetic binder as UF resin should be avoided to reduce the formaldehyde emission. In that case two possibilities can be considered: the plant particles can be self-bound without addition of other binder than water; or they can be bound with the addition of a biobased adhesive. For binderless particleboards the process consists on taken advantages of chemical composition of the agroressources. The lignocellulosic compounds contained in plant particles undergo chemical changes during thermocompression with water according to the mechanisms described by Zhang et al. [11]. As also explained by Nasir et al. [12], during hot pressing, several reactions such as dehydration, hydrolysis and oxidation reactions are observed, especially on hemicelluloses, which are poor thermally stable compound. The residual compounds can produce good adhesive between plant particles interfaces. Nevertheless, the properties of particleboards thus bound are limited especially for boards with low density. That is why a lot of researchers turn towards the formulation of biobased adhesives. In a previous work binderless particleboards made of various blends of sunflower bark and flax shives have been studied and compared with same plant particles bonded with a classical UF resin [13]. These biosourced boards present poor mechanical properties especially due to a lack of internal cohesion. That is why in this study we have tried to improve the adhesion in the particleboards by addition of a biosourced adhesive.

In the search for alternatives to petroleum-based wood adhesives, efforts have been dedicated to develop adhesives by using phenolic substitutes based on wood extracts as tannin or lignin as described by Ang et al. [14] and Ji et al. [15], or lignin extracted from other agroressources as studied by Ghaffar et al. [16]. Ferreira et al. [17] proposed to use byproducts of wood pulping process as natural binder for particleboards and Privas et al. [8] worked with liginosulfonate. Other biobased compounds as polysaccharides can be used, for example starch or sodium alginate, Ji et al. [12] and Mati-Baouche et al. [6] studied chitosan as bio-adhesive in particleboards and Norström et al. [18] studied various plant gum. In many other studies proteins were used as biobased adhesives, for example soy proteins by Mo et al. [19], wheat gluten by Khosravi et al. [20] or bone glue by Nguyen et al. [5]. Casein, the protein from bovine milk obtained by precipitating from the milk after acid treatment, is available in large quantities. El Hajj et al. [7] have used casein as adhesive with flax shives. In this study the casein-based adhesive was used in high proportions in the composite material (50% to 70%). The results are interesting in terms of mechanical, thermal and acoustical properties but the resistance to humidity was still too low. For different materials, it has been demonstrated that casein or caseinate can provide other interesting properties, such as flame retardancy as shown by Alongi et al. [21] for cotton fabrics or antimicrobial effects as shown by Arrieta et al. [22] who mixed carvacrol or lysozyme with casein in edible films for food packaging. These

properties can also be interesting in building materials to which specifications in terms of resistance to fire and durability against microorganisms are required.

The study presented here reports on the formulation of an adhesive based on casein in aqueous solution and on the preparation of particleboards with this adhesive and using agricultural by-products; additionally, the casein based adhesive system was optimized according to the achieved mechanical properties of the particleboards. The optimized casein adhesive is then used to bind flax shives and sunflower bark of two different particle sizes in order to obtain particleboards of 500 kg.m⁻³ density. To evaluate the effects of the adhesive addition, these particleboards are compared with boards from the same plant particles but without any adhesive. All the particleboards are characterized by their mechanical, thermal and hygroscopical properties, which allow understanding the structure-property relationships of the plant particles with the adhesive and to conclude on the capacity of these materials to be used in construction according to EN 15197 [23].

2 MATERIALS AND METHODS

2.1 Raw materials

Agroressources

The flax shives used in this study are by-products of the production of flax fiber and came from the Northwest of France. Flax shives represent the woody part of plant stalks. They are used as animal litter and for particleboard manufacturing (only with synthetic resin as binder). This agricultural byproduct is very abundant in the North of France. In 2018, 115 000 tons of scutched flax have been produced from 98 000 hectares of grown flax. 50% of the scutched flax are flax shives and 50% are flax fibers. After harvesting the flax balls are stored in warehouses before to be scutched all the year round.

The sunflower bark is the external part of sunflower stalks. It can be obtained after separation of the sunflower pith which forms the internal part of the stalks. The sunflower bark used in this study came from the center-west of France. A small proportion of pith residues, which cannot be eliminated during the separation process, is present with the bark. Currently the sunflower bark is not at all valorized. It is left in the field after head harvesting. All the harvesting and industrial valorization chain must be carried out, but this agricultural byproduct presents a very high potential of valorization for agromaterials. In 2017, 550 000 hectares of sunflower have been grown in France. Between 1 and 2 tons of stalks can be harvested per hectare according to the cutting height.

The used agroressources are heterogeneous materials consisting essentially of structural compounds (cellulose, hemicelluloses, lignin) and, to a lesser extent, of non-structural compounds (other polysaccharides, proteins, water-soluble organic compounds and inorganic compounds). The chemical composition of an agro-resource

depends on its botanical origin, but also on the location of the agrosresource in the plant and on its growth and harvest conditions. These parameters also influence the physical structure of the agrosresource, such as its porosity, its apparent density, and its mechanical strength.

Biobased adhesive

In the case of the particleboards prepared without addition of any adhesive, the lignocellulosic compounds contained in the agrosresources act as binders. These lignocellulosic compounds come from the surface or the heart of the agrosresource particles and are activated by various chemical processes thanks to evaporation of the added water during the thermocompression process to create something which can be called an in-situ bond line. The exact nature of all these lignocellulosic compounds is not completely defined, it will be mainly hemicellulose and lignin, and some other non-structural compounds.

The other particleboards are bonded by the addition of an adhesive based on casein. The casein is the protein extracted from bovine milk. It is dissolved in a basic solution containing potassium hydroxide (KOH), thus forming a water soluble caseinate. For the quantities used in laboratory, casein and KOH came from Sigma Aldrich. For a larger production, a technical casein could be used directly from dairy plants.

Different rates of KOH compared to the mass of casein have been tested on panels formed with small flax shives. Similarly, different addition of casein during panel production has been tested (with fixed KOH rate, based on casein mass). Based on these results, an optimized formulation of the casein-KOH adhesive has been defined. The better results have been obtained with a large excess of alkali salt compared to the neutral solution of casein solubilized by KOH. This adhesive formulation was used to compare panels with various types of agrosresources and binderless panels.

In order to compare this caseinate with the intended proportions of alkali salt also a commercial casein salt was used. It is a sodium caseinate purchased from Sigma Aldrich and used in the boards at the same level as the optimized casein-KOH formulation.

2.2 Particleboards manufacturing

The raw particles of flax and sunflower were crushed and then sieved to obtain two batches of particles of different sizes. The small particles were sieved between 0.5 and 2 mm while the big particles were sieved between 2 and 5 mm. The plant particles were conditioned at ambient temperature and 50% relative humidity during at least 48h before being used. In these conditions the particles show a moisture content of approximately 8%. In a first step the proportion of casein used in the adhesive and the proportion of KOH added to the casein to form a caseinate were fixed by testing various formulations on boards made of small flax shives only. Table 1. summarizes the different formulations used in order to optimize the adhesive based on casein with KOH.

Then, in a second step, particleboards were made with big or small particles of flax shives or sunflower bark and bounded with either the adhesive system based on casein and KOH at the previously optimized proportions, or the commercial caseinate-based adhesive or without any binder addition, for a total of 12 different boards. Figure 1 summarizes the various parameters studied in the biosourced particles boards in the second step. The quantity of material used was calculated in order to obtain a thickness of 15 mm and a density of 500 kg.m⁻³ for all boards. 5 boards were made for each formulation and for each test the samples were taken from all boards of a same formulation.

Tab.1: adhesive formulations studied in small flax shives boards

% KOH (compared with casein)					with casein: 12% w/w of the board
2	4	6,7	13,3	20	
% casein (of board mass)					with KOH: 20% w/w of casein
3	6	9	12	15	




Fig. 1 : Diagram of the parameters varying in the studied boards in the second step

A commercial board made of flax shives with a synthetic binder is used as a reference. It is used as door panel, partition wall and for furniture manufacturing. This reference board is made of three layers: the core layer is made of big flax shive particles and both face layers are made of small flax shive particles. This commercial board is bonded with 18% (w/w) of urea-formaldehyde resin (calculated on dry basis) and its density is 530 kg.m⁻³. That is why we choose a target density of 500 kg.m⁻³ for the new boards that we studied, and we tested biosourced binder amounts up to 18% (w/w) (15% of casein with 3% of KOH). All the measured properties of the laboratory-made boards are compared with the same properties of the commercial reference board.

The plant particles blended with the bio-based adhesive (14.5% mass/panel mass after optimization) or with water (80% mass/plant particles mass) were thermocompressed at 190°C in a mold during 20 minutes for the panels containing casein or caseinate based adhesive and 40 minutes for the panel with water, for boards of 15 mm thickness. This process needs some heating time because of the water to evaporate. For the binderless boards, a lot of water is added to the vegetal particles to generate vapor during hot pressing in order to extract some natural compounds that will act as binder between particles. 80% of the vegetal particles mass for the added water is reasonable considering that these particles are able to absorb more than 300% of their mass. In the boards using the biosourced binder, this binder is casein dissolved in basic aqueous solution. Water must be evaporated but there is less water than in the binderless boards so shorter evaporation time. It must also be considered that the

mold used is fully closed, thereby restricting evaporation. In an industrial production, larger presses with open edges are used, speeding up the water evaporation so reducing the hot-pressing time.

In the literature some solutions are proposed to reduce the thermopressing time, such as drying the mixture of vegetal particles with aqueous adhesive solution in an oven (during 24h at 100°C) to remove a part of the water before the thermopressing [5]. Another solution, studied by Mati-Baouche et al., is to dry the boards in an oven (during 50h at 50°C) after a short compression of 1 min. In all cases more time is necessary to remove water from binderless boards or from boards made with an aqueous adhesive than to cross-link a synthetic resin.

In the laboratory-scale mold, spacers are utilized to stop the closure of the mold in order to obtain a fixed panel volume (150 x 150 x 15 mm) and so the target density. The mat of vegetal particles with the binder of initially approximately 70 mm high (particles compacted by hand) was compressed until the final thickness of 15 mm. The pressure is applied on the spacers and not directly on the vegetal matter, so the pressure applied on the board is not known as soon as the spacers have been reached. Figure 2 shows the surface of the boards made of big flax particles and big sunflower ones bound with the casein-based adhesive.



Fig. 2 : Particleboards made of big sunflower bark on the left and made of big flax shives on the right.

2.3 Particleboards characterization

Mechanical behavior by bending tests

Three-point bending tests were carried out on each particleboard with a universal mechanical property testing machine (TA.XTplus texture analyser). Samples of 15 cm long are put on two supports spaced out by 10 cm. The sample dimensions were 150x30x15 mm³. The ratio between length and thickness of these samples does not allow the internal shear loads to be neglected but we were limited by the mold dimensions and we couldn't make longer boards at laboratory scale. Nevertheless, all measurements were realized in the same conditions, the results are therefore comparable between the studied biosourced boards and the reference board. A deflection rate of 6 min.min⁻¹ was applied in the middle of the sample. The required force to deform them was measured using a 500 N load cell. They were conditioned at 50% relative humidity before testing. The bending tests were performed always on the same side of the boards, in relation to the direction of the thermocompression. Figure 3

shows a photography of a flax board sample for the bending test. On picture (a) we can see the surface and the cross section of the sample cut with a bandsaw while picture (b) shows the fracture section after the bending test. The picture on the Figure 3(a) corresponds to a board sample after the bending test. That is why this sample is warped. This distortion is the result of breakage by bending test. To observe the fracture section as shown on the Figure 3(b), a much longer displacement was applied on the sample after the first breakage. The tests were repeated five times, at ambient temperature. The three-point bending test allows determining the modulus of rupture (MOR) and the modulus of elasticity (MOE).



Fig. 3 : Photography of a flax board sample after the bending test: surface and cross section (a), fracture section (b)

Internal bond

Internal bonding strength (IB in N.mm^{-2}) corresponds to the energy required to break the sample by z-directional tensile test. It gives an estimation of the fiber-to-fiber bond. The IB was measured on five squared samples ($50 \times 50 \times 15 \text{ mm}^3$) of each particleboard. Prior to testing, the samples were conditioned at 50% relative humidity then glued onto stainless steel supports with a hot melt. These supports were positioned in the holders of the TA.XTplus texture analyser. A loading rate of 3 mm.min^{-1} was applied until failure of the sample. For each test the occurrence of the failure inside the sample and not at the interface between the sample and the steel support was checked. If a failure occurred at the interface, just between the adhesive joint and the sample or between the adhesive joint and the steel support, it was seen as artificial experimental defect, and the test was not considered for the results calculated.

Thermal conductivity

The thermal conductivity of the particleboards was measured with a Heat Flow Meter HFM 436 Lamda from Netzch. The sample size was $150 \times 150 \times 15 \text{ mm}^3$. The measurements were performed in a steady state at 20°C with a temperature gradient between the hot and the cold plate of 20°C and repeated at least 3 times for each material.

Hygroscopic behavior

Thickness swelling (TS) and water absorption (WA) were measured on samples of 50x50x15mm³, after fully immersion in 20°C distilled water for 24 hours. After removal from the water bath, excess of water was removed with sorbent paper tissues. The thickness of the samples was measured by a caliper in the middle of each sample before and after the water immersion. The water absorption was determined by weighting the samples before and after the immersion, on a scale with 0.1 mg precision. The measurements were repeated on five samples for each particleboard.

Resistance to fire

The resistance to fire of the particleboards made of flax shives and sunflower bark was tested according to EN ISO 11925-2 [24]. The measurements were realized in a dedicated chamber where samples of 90*290*15mm³ were exposed to a propane flame inclined by 45° on the lower edge of the sample during 30 s. Measurements were realized in triplicate on each board. After exposure to the flame, the absence of ignition and of flaming droplets was observed and the height of the damaged zone was measured. Figure 4 shows the installation to realize this measurement and an example of the damage zone after the test on a sunflower board.



Fig. 4 : installation for test of resistance to fire and example of some boards after the test

3 RESULTS AND DISCUSSION

3.1 Biobased adhesive formulation

First tests have been carried out to formulate the adhesive based on casein. Casein can be dissolved in water only in a basic solution, where the casein forms a caseinate. In order to fix the proportion of KOH which is required to obtain the best performing casein adhesive, different KOH rates based on casein were tested. The efficiency of the various adhesives was evaluated by comparison of the mechanical properties of the produced

boards. For the tests of the adhesive formulations, only small flax shives were used in the boards. Tab. 2 presents the maximal bending strength (MOR) of the boards containing 12% (mass / panel mass) of casein and various KOH rates (the proportion of solid KOH is based on solid casein mass) dissolved in 80 ml of water. The pH of the casein-KOH solution is neutral for 4% KOH but the maximal bending strength of these panels increased significantly with increasing KOH addition giving alkaline behavior. The better mechanical properties of the boards made with the casein-based adhesive with high level of KOH can be explained by the lower viscosity of this adhesive solution. The viscosity of the casein/KOH solution decreases with the increase of the proportion of KOH. A lower viscosity of the adhesive solution allows better repartition of the adhesive on the flax particle surfaces, leading to better adhesion and better mechanical properties. According to these results, the highest KOH rate (20%) gave the highest MOR (10.5 MPa) and was selected for the tests with different addition of casein as adhesive.

Tab.2: MOR and IB of small flax shive boards containing 12% (m/board m) of solid casein with various solid KOH rates and of boards containing 20% (m/casein m) of KOH and various casein rates.

rate of KOH									
compared with		2		4		6.7		13.3	
casein mass (%)									
Casein at 12% of board mass	MOR	<i>sd</i>	MOR	<i>sd</i>	MOR	<i>sd</i>	MOR	<i>sd</i>	MOR
	(MPa)		(MPa)		(MPa)		(MPa)		(MPa)
	5.7	0.5	6.7	0.7	7.1	0.6	8.9	1.0	10.5
									0.9
rate of casein									
compared with		3		6		9		12	
board mass (%)									
KOH at 20% of casein mass	MOR	<i>sd</i>	MOR	<i>sd</i>	MOR	<i>sd</i>	MOR	<i>sd</i>	MOR
	(MPa)		(MPa)		(MPa)		(MPa)		(MPa)
	4.8	0.4	7.4	0.7	11.2	1.1	10.5	0.9	10.9
					IB	<i>sd</i>	IB	<i>sd</i>	IB
					N.mm ⁻²		N.mm ⁻²		N.mm ⁻²
					0.11	0.02	0.20	0.03	0.20
									0.04

The second step of the adhesive formulation was to fix the casein proportion in the board. The total proportion of binder in the board (casein + KOH) was limited with 18% (calculated as solid compound versus total board matter stabilized at 8% RH), which is the same value as for the industrial control panel. In the second part of Table 2, the MOR of boards containing various mass proportion of casein (always with 20% solid mass of KOH / solid casein

mass) is presented. We can observe that the maximal strength increases with the casein rate until 9% casein and then the panel bending resistance is approximately constant between 9% and 15% of casein with 10.5 to 11.2 MPa.

In order to make a choice between 9%, 12% or 15% casein in the flax shive boards, we compared their IB (Table 2). The result obtained with 9% casein was significantly lower than these obtained for both other boards. With 12% and 15% casein in the boards, the internal bond was 0.20 N.mm^{-2} , fulfilling the requirements of EN 15197: minimum IB of 0.13 N.mm^{-2} for the first class of boards and 0.20 for the second. Since the IB were the same for 12% and 15% casein, the lower addition (12%) was selected for further tests. The selected 20% KOH corresponds to 2.4% of KOH based on board mass containing 12% of casein. Knowing that the adhesive solution of casein/KOH is neutral for 4% KOH (compared to casein mass), this is the quantity used to form the caseinate. It can be considered that the KOH added beyond is in excess in the solution. For the adhesive formulation optimized with 20% KOH compared to casein mass, 16% are excess of KOH. It corresponds to 1.9% of the total board mass, which is free potassium hydroxide. This adhesive formulation was used in the further tests with variations of botanic origin of the particles and of particle sizes. The obtained boards were compared with binderless boards and with boards made with a commercial sodium caseinate based adhesive.

3.2 Comparison of board properties with or without adhesive

Mechanical behavior by bending tests

Table 3 presents MOR and MOE obtained by bending test of the different studied panels. A large difference is observed between the panels bound with the biobased adhesive or without. It seems interesting to realize a particleboard without externally added adhesive because this corresponds to valorization of only the agroresource and its internal composition including inherent chemicals. It has been demonstrated that suitable compounds must be extracted from the plant matter by the vapor and then activated by heat to act as binder and to obtain cohesive bond strength. Pintiaux et al. [25] explain that water extractable compounds are responsible for the self-adhesion capacity of agro-resources during the thermomechanical steam treatment of binderless particleboards. These water extractable compounds come from degradation of cellulose and hemicelluloses during the steam treatment, which can partially hydrolyze them to simple soluble sugars. Lignin is another important chemical for the binderless adhesion process. The joint action of moisture and heating causes on lignin some degradation, softening and plasticization leading to new linkage capability. It is also reported that with heat and pressure lignin melts at the surface of fibers and binds the fibers together [26]. The vapor can be obtained by vaporization of the water previously blended with the plant particles or by direct steam injection into the mold during pressing. Our press is not equipped with system allowing direct steam injection. That's why cold water is added to vegetal particles and heated for a long time in order to generate vapor. Direct steam injection and a press with open edges, facilitating vapor extraction) could reduce the pressing time of binderless boards. Despite too long process

time, properties of our binderless boards were studied to highlight the differences to boards with addition of a biosourced binder.

In this study the binderless boards showed sufficient cohesion strength to enable manual handling of the pressed boards (they can be manipulated without visible alterations), but the bending test shows that their MOR and MOE are very low with 0.8 to 3.3 MPa for the MOR and 127 to 274 MPa for the MOE. The internal bond is also very low with 0.02 to 0.04 N.mm⁻², showing an important lack of internal cohesion between particles despite a certain adhesion achieved by the extractable compounds during the thermocompression process. Nevertheless, we can notice that mechanical resistance is slightly better for the binderless panels made of big flax shives than for the three others. Comparable results were obtained in a previous study carried out by Mahieu et al. [13] in which flax shives and sunflower bark were used in different proportions in three-layer binderless particleboards. This study showed that with a MOR of 3.8 MPa, binderless boards made of flax shives present interesting mechanical resistance in comparison with flax boards made with UF resins by the same laboratory scale thermopressing process (with MOR of 1.1 MPa). In the present study the same process can lead to panels with very much better MOR when a biobased binder is added.

Boards containing the casein based adhesive and made of big plant particles present better MOR and MOE compared to small particles. Commercial three-layer particleboards are mainly made of big particles, both face layers with small particles being used for the surface behavior to limit the access of water, however not for mechanical performances.

The results of bending tests also show a difference according to the botanical origin of the plant particles. At the same particle size and same pressing process, the panels made of flax shives always present higher MOR and MOE than the panels made of sunflower bark. The morphology of these agroresources can explain this result. The flax shives are fine and flexible particles (thickness between 0.1 and 0.4 mm) whereas sunflower bark particles are thicker (between 0.3 to 3.5 mm) and hard and brittle. With a maximal bending strength of 8.1 MPa, the panel made of big sunflower bark with casein-based adhesive could be used to replace classical wood-based particleboards in applications for non-load bearing panels (first class of requirements described in EN 15197). Non-load bearing panels can be used for furniture or covering but not for structural applications. With a maximal bending strength of 13.7 MPa and a MOE of 1216 MPa, the panel made of big flax shives with casein-based adhesive presents better bending properties than the commercial reference panel made with three layers of flax shives with UF resin. This board could be used to replace classical particleboards in applications corresponding to the first and the second classes of requirements described in EN 15197. According to this standard, the first class concerns flaxboards for general purpose in dry conditions (usually for filling purposes), while the second class concerns non-load bearing flaxboard for use in dry conditions (usually for further processing, such as veneering). The bending properties of the commercial reference board are closer to that of the biobased board made of small flax shives with casein adhesive. However, IB of the commercial board is higher compared to all biobased bonded boards (0.32 compared to 0.17 to 0.24 N.mm⁻²). EN 15197 requires an IB of 0.13 N.mm⁻² for the

first class of application and 0.20 N.mm^{-2} for the second. Thus, IB obtained for the biobased boards is in the range of the limits and principally would envisage use of these boards in replacement of the classical board. The biobased boards bonded with the sodium caseinate adhesive present slightly better bending properties than the casein/KOH-based in the case of boards made with sunflower bark (small or big), but the bending properties of the boards made with flax shives are lower with the caseinate adhesive than with the casein/KOH one. The internal bond is slightly higher with the sodium caseinate for all boards. Thus, the type of caseinate used in the adhesive formulation (commercial sodium salt or made with an excess of potassium hydroxide) could be adapted according to the agresource used and the expected mechanical properties.

Tab. 3: Modulus of rupture, modulus of elasticity, internal bond and thermal conductivity of the different studied panels

adhesive	agro-resource	particle size	MOR (MPa)		MOE (MPa)		$\lambda \text{ (mW.m}^{-1}\text{.K}^{-1}\text{)}$		IB (N.m^{-2})	
			average	standard deviation	average	standard deviation	average	standard deviation	average	standard deviation
casein (12%) KOH (2.4%)	flax	small	10.5	0.9	1003	109	84.1	0.7	0.20	0.02
	shives	big	13.7	1.1	1216	106	79.7	0.6	0.20	0.02
	sunflower	small	5.8	0.4	692	94	89.3	0.8	0.17	0.03
	bark	big	8.1	1.0	659	79	84.5	0.6	0.18	0.04
casei- nate (14.5%)	flax	small	8.4	1.0	738	93	82.9	0.8	0.23	0.03
	shives	big	12.3	1.0	1106	81	80.3	0.9	0.20	0.03
	sunflower	small	6.5	0.6	769	88	85.3	0.8	0.24	0.02
	bark	big	9.8	0.3	992	81	82.5	0.7	0.22	0.01
binder- less	flax	small	1.2	0.2	165	14	76.7	1.2	0.04	0.02
	shives	big	3.3	0.4	274	22	72.0	1.1	0.04	0.02
	sunflower	small	0.8	0.1	127	18	77.9	1.0	0.02	0.01
	bark	big	1.0	0.0	139	12	72.9	1.1	0.02	0.01
Commercial reference										
flax board with UF resin			11.7	0.4	1040	78	81.6	0.8	0.32	0.02

Insulation properties

Thermal conductivity is usually directly connected to material density. The lower the density, the lower the thermal conductivity, thanks to the air insulation capability. Although all studied panels have the same target density (500 kg.m^{-3}) and final densities of $498 \pm 10 \text{ kg.m}^{-3}$, the measured thermal conductivities vary. A significant difference

is observed between boards made with both biobased adhesive and without binder. As shown in Table 3, the thermal conductivities of the binderless panels are between 72 and 78 $\text{mW.m}^{-1}.\text{K}^{-1}$ whereas these of panels which contain the biobased adhesives are between approximately 80 and 90 $\text{mW.m}^{-1}.\text{K}^{-1}$. This can be due to the formation of thermal bridges by the adhesive but also to the replacement of a part of the plant particles by the adhesive. The plant particles present a honeycomb structure with fine cavities full of air, the best insulator, whereas the adhesive is denser. This also explains the results presented in Table 4: the thermal conductivity increases with the increase of adhesive rate in the panel made of small flax shives. El Hajj et al. [7] come to the same conclusion on agrocomposites made by casein based binder with flax shives (50% to 70% of binder) when boards of same densities are compared. Viel et al. [9] well show the influence of the addition of a binder on the thermal conductivity in particleboards made of hemp shives or corn cob with various binders, but they obtain very high thermal conductivity for particleboards of density about 500 kg.m^{-3} with around $150 \text{ mW.m}^{-1}.\text{K}^{-1}$.

Tab. 4: Thermal conductivity λ of panels made of small flax shives with different casein rates (and 20% (w/casein w) of KOH) at 500 kg.m^{-3}

casein rate in the panel (%)	$\lambda \text{ (mW.m}^{-1}.\text{K}^{-1})$	
	average	standard deviation
9	81.8	0.8
12	84.1	0.7
15	88.2	0.7

The particleboards include two types of porosity: the internal porosity of the plant material and the porosity induced by the arrangement of the particles in the board, which is linked to the board density. At the same board density, the internal porosity of the plant particles has a more important role in the material insulation capacity than the external porosity when comparing different plant materials. This observation is confirmed by the difference observed between thermal conductivities λ of comparable panels made of flax shives or sunflower bark. The bulk density of the flax shives is 100 kg.m^{-3} whereas that of sunflower bark is 180 kg.m^{-3} . As shown by Mahieu et al. [25], the flax shives show more uniform pores of homogeneous and finer sizes than the sunflower bark which is made of pores of various and coarser sizes with thicker walls. This may explain the higher bulk density measured for the sunflower bark. The sunflower bark includes much less internal porosity than the flax shives. Knowing that the internal porosity of the plant particles is the basis of the thermal insulation capacity of the particleboards, it may explain that the boards made of sunflower bark are less insulating and present so slightly higher λ than these made of flax shives at the same board density if the same quantity of adhesive is used. Moreover, as shown by Shynar et al. [27] on porous ceramics, the pore size has an influence on the thermal conductivity at equivalent porosity: a coarser microstructure exhibits higher thermal conductivity than a finer one.

In the vegetal particles the finer pores of the flax shives lead to lower thermal conductivity so better thermal insulation capacity for the flax boards than for the sunflower ones, which have coarser pores. The difference of λ between sunflower and flax particles is less significant for binderless boards. The particle size has also an influence on λ at the same board density. In all case λ is lower with big particles than with small ones. On the one hand, the thermal bridges are more numerous with small particles, and on the other hand, due to the crushing, a part of the initial internal porosity disappears in the small particles. A slight decrease of λ can be observed with the sodium caseinate adhesive in comparison with the casein-KOH adhesive but the difference is low. According to an analysis of variance (ANOVA test) the variation of λ between boards with both different adhesives is significant for sunflower boards (with probability values less than 5% : 4.10^{-4} and 4.10^{-3} respectively for small and big sunflower bark). However, the λ variation is not significant for the flax boards with probability values more than 5% : 0.07 and 0.3 respectively for small and big flax shives. The lowest λ is given for the board with big flax shives without binder with $72 \text{ mW.m}^{-1}.\text{K}^{-1}$. The better λ for the boards bound with an adhesive is reached for the small flax shives with $80 \text{ mW.m}^{-1}.\text{K}^{-1}$ (average of λ for boards with both adhesives). It is significantly less than the λ of the reference board made of flax shives with UF resin ($81.6 \text{ mW.m}^{-1}.\text{K}^{-1}$) with a probability value of 0.008.

Hygroscopic properties

Table 5 presents water absorption (WA) and thickness swelling (TS) after 24h. The plant particles present naturally a high affinity with water and are very sorbent due to their high porosity. In binderless boards the cohesion of the particles is based on wood inherent chemicals extracted during the thermocompression process by water and steam. A smaller part of these water-soluble compounds extracted during the process can further react under influence of temperature and time to give insoluble materials, but the greater part remains soluble. These soluble adhesive components might be again dissolved in water during the immersion, such as sugars from the degradation of hemicellulose or some degradation products of lignin. The binderless boards sorb high quantities of water, 220 to 270% of the board initial mass and swell strongly, from 50 to 100% of the initial thickness, which is not surprising without addition of any hydrophobic agent. Consequently, the binderless panels present very bad cohesion after the water immersion. On the contrary, the panels containing the biobased adhesives present much better cohesion after the immersion. Due to the addition of the biobased adhesives TS is reduced (from 50-100% to 18-38%) and is in the order of magnitude of particleboard based on wood particles but without addition of hydrophobic agents such as paraffin. WA is also reduced but remains still high (100-180%). A significant difference of the hygroscopic properties is observed between panels based on small or big particles. In all cases TS and WA are higher for big particles compared to small ones. This fact can be explained by the bigger size of the pores in the coarse plant particles. Except from the coarse flax shives panel bound with casein-KOH, the panels made of sunflower bark seem to sorb more water and to swell more than the panels made of flax shives. The panels made with the sodium caseinate sorb and swell slightly more than the panels made with the casein-KOH adhesive. Nevertheless we can notice that one biosourced board (with small flax shives bound with

casein/KOH adhesive) shows, with 18% of TS and 103% of WA, similar values of TS and WA as the commercial reference board made of flax shives with UF resin with 15% of TS and 99% of WA. This means that there is a good chance for this biosourced board to replace boards bonded with synthetic binder. However, the press time remains to be improved for the introduction of such bio-based boards into industrial production. The board made of big flax particles, shows good mechanical properties but insufficient behavior towards water. Thus, new attempts are necessary to improve the resistance towards water to be able to use them in a wet environment. The panels based on flax shives and sunflower bark with biobased adhesive may still be used for applications in dry environment according to the standard EN 15197.

Tab. 5: Water Absorbtion (WA) and Thickness Swelling (SW) of the different panels after 24h immersion in water.

			Water Absorbtion (%)		Thickness Swelling (%)	
adhesive	agro-resource	particle size	average	standard deviation	Average	standard deviation
casein (12%)	flax shives	small	103	12	18	1
		big	149	8	23	1
KOH (2.4%)	sunflower	small	140	9	26	3
	bark	big	141	14	30	3
caseinate (14.5%)	flax shives	small	133	9	25	1
		big	142	15	30	2
	sunflower	small	163	12	35	3
	bark	big	179	9	38	3
binderless	flax shives	small	262	5	53	1
		big	245	11	74	1
	sunflower	small	274	18	84	4
	bark	big	221	7	101	8
Commercial reference			99	1	15	1

Resistance to fire

As shown by Mahieu *et al.* [13], the height of the damaged zone by fire for the three layers binderless flax board at 500 kg.m⁻³ is 9.8 cm and 8.7 cm for the sunflower one, whereas for boards bound with UF resin the height of the damaged zone is 13.0 cm for the flax board and 11.3 cm for the sunflower board. Figure 5 presents the height of the damaged zone by fire, measured with the same protocol on the commercial reference board and on the boards bound with the casein-KOH adhesive or the sodium caseinate adhesive. The boards containing casein or

caseinate present clearly a much smaller height of the zone damaged by fire. This height decreases from 13 cm for the reference board (bound with UF resin) to between 9 and 10 cm for the binderless boards [13]. This decrease is due to a difference of the flame propagation in relation with the nature of the adhesive. The test consists on measuring the damaged zone by the flame on the board surface and does not necessarily reflect the degradation of material properties or the thickness of the damaged layer. The adhesive based on components extracted from water during the thermocompression process seems to react to fire slightly less than the UF resin, since they do not contain nitrogen, as compared to a UF resin. The height of the damaged zone decreases much more for the boards containing casein or caseinate down to between 3.3 to 4.3 cm. This result is due to the flame-retardant property of the casein, as shown by Alongi [21]. For all studied particleboards, there is no significant difference for the damaged zone height between flax or sunflower or between the particle sizes. A small but significant difference (probability value of 0.009 by ANOVA test) can be observed between the adhesives: the boards made with the casein-KOH adhesive present a damaged zone smaller of approximately 0.7 cm than the caseinate-made boards (average heights of respectively 3.4 cm and 4.1 cm). Whereas the commercial sodium caseinate contents only 3% of sodium, the excess of KOH in the casein-KOH adhesive leads to an increase of the flame-retardant property of the casein. This fact might be explained by an action of the excess of hydroxide on the plant material. This action could be assimilated to the classical use of alkali treatment to improve the surface of plant fibers, generally leading to improvement of the fiber thermal stability as shown by Parre *et al.* on banana fibers [28]. This flame-retardant property of the casein-based adhesive consists of a large advantage for the use of this adhesive in replacement of the synthetic resin in particleboards.




Fig. 5: Height of the damaged zone caused by fire, for the different boards.

4 CONCLUSION

In order to understand the structure-property relationships of particleboards made from agricultural by-products, two agro-resources from different botanical origin (flax shives and sunflower bark) at two different particle sizes and two types of casein adhesive as well as a binderless version have been tested.

The mechanical strength of the particleboards depends on the interactions between the surface of the particles and the used binders. Vapor extractable compounds produced by lignin and hemicellulose degradation with steam are responsible for the self-adhesion capacity of the agroresources during thermocompression of the binderless particleboards. By using a biobased adhesive, the mechanical resistance is improved and allows adapting the formulation to the required behaviors of the final material, such as improvement of the water and fire resistance, while keeping good thermal properties.

The formulation of biobased adhesive based on casein has been optimized according to the mechanical properties of particleboards made of flax shives. It appears that an excess of KOH in comparison with casein leads to better mechanical properties of the panels due to a lower viscosity of the adhesive. The use of a commercial sodium caseinate showed comparable or partly slightly lower board properties. A proportion of even less than 15% (w/w) of biobased adhesive in the particleboards is enough to obtain sufficient mechanical properties. The comparison of the different boards produced showed that:

- Big particles provide better mechanical properties than small ones.
- In all cases flax-shive panels are more resistant to bending than sunflower bark-based panels.
- Addition of casein and caseinate based adhesives leads to particleboards with much better mechanical properties than binderless ones.
- Using caseinate adhesive by blend of casein with an excess of KOH leads to slightly better properties than using a commercial sodium caseinate (mechanical properties and resistance towards water and fire).

Casein-based adhesive improve the board resistance towards water compared to binderless boards. TS is reduced by factor approx. 3. Nevertheless, TS and WA still need to be improved. The binderless boards show lower thermal conductivity due to the presence of only plant material with a porous structure, whereas in the boards containing some adhesive, some porous plant material is replaced by the adhesive as a denser material. But the binderless boards suffer from too low mechanical and hygroscopical properties and the extremely long press time needed to see at least some bonding effect.

Finally, all measured properties demonstrate the interest of using a casein or caseinate-based adhesive in comparison with the binderless boards, especially for their very good flame-retardant property. Both studied

522 aggroresources could be used in particleboards for non-load bearing applications in a dry environment. Big flax
523 shives seem nevertheless more suitable for particleboard manufacturing but need optimization of the formulation
524 and the production process.
525

526 REFERENCES

-
- [1] Vo L.T.T., Navard P. Treatments of plant biomass for cementitious building materials – A review, *Construction and Building Materials*. 2016; 121, 161-176. <http://dx.doi.org/10.1016/j.conbuildmat.2016.05.125>
- [2] Laycock B., Nikolic M., Colwell J. M., Gauthier E., Halley P., Bottle S., George G. Lifetime prediction of biodegradable polymers, *Progress in Polymer Science*, 2017; 71, 144-189.
<http://doi.org/10.1016/j.progpolymsci.2017.02.004>
- [3] Klimek P., Wimmer R., Meinschmidt P., Kúdela J. Utilizing Miscanthus stalks as raw material for particleboards, *Industrial Crops & Products*. 2018; 111, 270–276. <http://dx.doi.org/10.1016/j.indcrop.2017.10.032>
- [4] Zhang L., Hu Y. Novel lignocellulosic hybrid particleboard composites made from rice straws and coir fibers, *Materials & Design*. 2014; 55, 19-26. <https://doi.org/10.1016/j.matdes.2013.09.066>
- [5] Nguyen D.M., Grillet A.-C., Diep T.M.H., Bui Q.B., Woloszyn M. Influence of thermo-pressing conditions on insulation materials from bamboo fibers and protein-based bone glue, *Industrial Crops and Products*. 2018; 111, 834-845. <http://dx.doi.org/10.1016/j.indcrop.2017.12.009>
- [6] Mati-Baouche N., De Baynast H., Lebert A., Sun S., Lopez-Mingo C.J.S., Leclaire P., Michaud P. Mechanical, thermal and acoustical characterizations of an insulating bio-based composite made from sunflower stalks particles and chitosane, *Industrial Crops and Products*. 2014; 58, 244-250.
<https://doi.org/10.1016/j.indcrop.2014.04.022>
- [7] El Hajj N., Dheilly R.M., Goullieux A., Aboura Z., Benzeggagh M.L., Quéneudec M. Innovant agromaterials formulated with flax shaves and proteinic binder: Process and characterization, *Composites: Part B*. 2012; 43, 381–390. <https://doi.org/10.1016/j.compositesb.2011.05.022>
- [8] Privas E., Navard P. Preparation, processing and properties of lignosulfonate-flax composite boards. *Carbohydrate Polymers*. 2013; 93, 300-306. <http://dx.doi.org/10.1016/j.carbpol.2012.04.060>
- [9] Viel M., Collet F., Lanos C. Development and characterization of thermal insulation materials from renewable resources, *Construction and Building Materials*. 2019; 214, 685–697.
<https://doi.org/10.1016/j.conbuildmat.2019.04.139>

-
- [10] Fiorelli J., Bueno S. B., Cabral M. R. Assessment of multilayer particleboards produced with green coconut and sugarcane bagasse fibers, *Construction and Building Materials*. 2019; 205, 1–9.
<https://doi.org/10.1016/j.conbuildmat.2019.02.024>
- [11] Zhang D., Zhang A., Xue L. A review of preparation of binderless fiberboards and its self-bonding mechanism, *Wood Science and Technology*. 2015; 49, 661–679. <https://doi.org/10.1007/s00226-015-0728-6>
- [12] Nasir M., Khali D.P., Jawaid M., Tahir P.M., Siakeng R., Asim M., Khan T.A. Recent development in binderless fiber-board fabrication from agricultural residues: A review, *Construction and Building Materials*. 2019; 211, 502–516. <https://doi.org/10.1016/j.conbuildmat.2019.03.279>
- [13] Mahieu A., Alix S., Leblanc N. Properties of particleboards made of agricultural by-products with a classical binder or self-bound, *Industrial Crops and Products*. 2019; 130, 371-379.
<https://doi.org/10.1016/j.indcrop.2018.12.094>
- [14] Ang A. F., Ashaari Z., Lee S. H., Md Tahir P., Halis R. Lignin-based copolymer adhesives for composite wood panels—A review, *International Journal of Adhesion and Adhesives*. 2019; 95, 102408.
<https://doi.org/10.1016/j.ijadhadh.2019.102408>
- [15] Ji X., Guo M. Preparation and properties of a chitosan-lignin wood adhesive, *International Journal of Adhesion and Adhesives*, 2018; 82, 8-13. <https://doi.org/10.1016/j.ijadhadh.2017.12.005>
- [16] Ghaffar S.H., Fan M. Lignin in straw and its applications as an adhesive, *International Journal of Adhesion and Adhesives*. 2014; 48, 92-101. <http://dx.doi.org/10.1016/j.ijadhadh.2013.09.001>
- [17] Ferreira A.M., Pereira J., Almeida M., Ferra J., Paiva N., Martins J., Magalhães F.D., Carvalho L.H. Low-cost natural binder for particleboards production: study of manufacture conditions and stability. *International Journal of Adhesion and Adhesives*, 2019; 93, 59-63. <https://doi.org/10.1016/j.ijadhadh.2019.01.019>
- [18] Norström E., Fogelström L., Nordqvist P., Khabbaz F., Malmström E. Gum dispersions as environmentally friendly wood adhesives, *Industrial Crops and Products*. 2014; 52, 736– 744.
<http://dx.doi.org/10.1016/j.indcrop.2013.12.001>
- [19] Mo X., Sun X.S. Soy proteins as plywood adhesives: formulation and characterization, *Journal of Adhesion Science & Technology*. 2013; 27, 2014-2026. <http://dx.doi.org/10.1080/01694243.2012.696916>
- [20] Khosravi S., Nordqvist P., Khabbaz F. Johansson M. Protein-based adhesives for particleboards – Effect of application process, *Industrial Crops and Products*. 2011; 34, 1509-1515.
<https://doi.org/10.1016/j.indcrop.2011.05.009>

-
- [21] Alongi J., Carletto R.A., Bosco F., Carosio F., Di Blasio A., Cuttica F., Antonucci V., Giordano M., Malucelli G. Caseins and hydrophobins as novel green flame retardants for cotton fabrics, *Polymer Degradation and Stability*. 2014; 99,111-117. <https://doi.org/10.1016/j.polymdegradstab.2013.11.016>
- [22] Arrieta M.P., Peltzer M.A., López J., Del Carmen Garrigós M., Valente A.J.M., Jiménez A. Functional properties of sodium and calcium caseinate antimicrobial active films containing carvacrol, *Journal of Food Engineering*. 2014; 121, 94–101. <https://doi.org/10.1016/j.jfoodeng.2013.08.015>
- [23] EN 15197, AFNOR, Wood based panels, specifications for flaxboards, 2007, 15p.
- [24] EN 11925-2, AFNOR, Reaction to fire tests — Ignitability of products subjected to direct impingement of flame — Part 2: Single-flame source test, 2010, 26p.
- [25] Pintiaux T., Viet D., Vandenbossche V., Rigal L., Rouilly A. Binderless materials obtained by thermo-compressive processing of lignocellulosic fibers: a comprehensive review, *BioResources*. 2015; 10, 1915-1963.
- [26] Okuda, N., and Sato, M. Manufacture and mechanical properties of binderless boards from kenaf core. *Journal of Wood Science*. 2004; 50, 53-61. <https://doi.org/10.1007/s10086-003-0528-8>
- [27] Shynar K., Jang-Hoon H., Rohit M., Young-Wook K., Kwang J. K. Effects of porosity on electrical and thermal conductivities of porous SiC ceramics, *Journal of the European Ceramic Society*. 2020; 40, 996-1004. <https://doi.org/10.1016/j.jeurceramsoc.2019.11.045>
- [28] Parre A., Karthikeyan B., Balaji A., Udhayasankar R. Investigation of chemical, thermal and morphological properties of untreated and NaOH treated banana fiber. *Materials Today*. 2020; 22, 347-352. <https://doi.org/10.1016/j.matpr.2019.06.655>